



# Majestic

Aqueous Gloss Media



## PPGWRADP: Everyday gloss microporous polypropylene w/ permanent adhesive

Designed to be used on applications such as window signs, boards or magnate material where adhesion and low maintenance is needed. Its microporous coating gives it the ability to reproduce photo quality images while maintaining good tear resistance.



### Benefits:

- Economical
- Water Resistant
- High Color Gamut with Instant Dry Coating
- Tear Resistant

### Applications:

- Best for Flat Mounting
- Window Signage
- Boards and Magnate Material
- Photo and Graphic Displays

#### TECHNICAL DATA: QM-PPGWRADP – EVERYDAY GLOSS MICROPOROUS POLYPROPYLENE W/ PERMANENT ADHESIVE

SURFACE FINISH:	Gloss	WHITENESS:	90 (CIE Ganz)
BASE MATERIAL:	Polypropylene	GLOSS MEASUREMENT:	38 +/- 10% by angle of 60°
ADEHESIVE MATERIAL:	Clear Acrylic Base Permanent	OPACITY:	96
LINER MATERIAL:	PET	DURABILITY:	<i>Indoor:</i> Up to 1 year <i>Outdoor:</i> Up to 6 months
LINER WEIGHT:	XX GSM +/- 10%	ROLL LENGTH:	100 FT.
LINER CALIPER:	X +/- .5 Mil	ROLL WIDTHS:	24", 36", 42", 50", 60"
FACE STOCK WEIGHT:	165 GSM +/- 10%	CORE:	3" with 2" Adapter
FACE STOCK CALIPER:	9 Mil +/- 1	PRINT SIDE:	Print Side Out
BRIGHTNESS:	90 (ISO Blue Whiteness)	INK RECOMENDATIONS:	AQUEOUS  LATEX  UV



This media is designed for digital printing applications using OEM printers with their accompanying OEM ink sets. Although designed for all printers using the aforementioned OEM matching ink sets; actual results may vary depending on printer model, age, print design, environmental conditions, and other factors. Exposure of a print to atmospheric pollutants, or to temperature, humidity, and / or lighting extremes can result in fading, color shifting, or other visual changes. The ideal conditions for printing and storage are a temperature of 70°F ±5°F and relative humidity of 50% RH ±3% RH. Our wide format media is guaranteed against manufacturing flaws and defects and is designed to resist printer jams when used properly. Storage: Up to one year if stored in proper conditions (cool, dry place 50-80°)

